

SYNTHETIC CALCIUM FLUORIDE

PARAMETER	M.U.	GUARANTED VALUE	TYPICAL VALUE	ANALYSIS METHOD
CaF ₂	%	45 min	48	XRF
CaSO ₄	%	-	25	XRF
CaCO ₃	%	-	5	MA 25
SiO ₂	%	-	5	XRF
Al ₂ O ₃	%	-	7	XRF
MgO	%	-	3	XRF
H ₂ O 110°C	%	-	35	Thermogravimetric

MA= FLUORSID METHOD

THIS DOCUMENT SHOWS FLUORSID'S STANDARD SPECIFICATION. UPON REQUEST, MODIFICATION MIGHT BE AVAILABLE.