

Data of issue: 2022-12-19 Rev. 02

SYNTHETIC CALCIUM FLUORIDE

PARAMETER	M.U.	GUARANTED VALUE	TYPICAL VALUES	ANALYSIS METHOD
CaF ₂	%	45 min	45 - 65	MI 26
CaSO ₄	%	-	10 - 30	MI 26
CaCO ₃	%	-	1,5 - 20	MI 18
SiO ₂	%	-	2 - 8	MI 26
Al ₂ O ₃	%	-	1 - 8	MI 26
MgO	%	-	0,5 – 3,5	MI 26
Fe ₂ O ₃	%	-	0,15 – 0,4	MI 26
H ₂ O 110°C	%	35 max	20 - 35	MI 23

PHYSICAL PROPERTIES	M.U.	TYPICAL VALUE	ANALYSIS METHOD
Particle size distribution			Dry sieve analysis
< 50 mm	%	100	UNI EN 933-1: 2012
< 5 mm	%	10	

MI= FLUORSID METHOD

THIS DOCUMENT SHOWS FLUORSID'S STANDARD SPECIFICATION. UPON REQUEST, MODIFICATION MIGHT BE AVAILABLE.